

Evalon[®] VSK

Superior Single-Ply Waterproofing

25

25 Year
Guarantee

50

50 Year
Service Life



BREEAM
Accredited



Trusted by
architects,
roofing
contractors
& developers

- ✓ Self-adhesive underside coating
- ✓ Bitumen-free & solvent-free
- ✓ Root-resistant
- ✓ High adhesive strength
- ✓ Quick and easy to install

- ✓ Bitumen compatible
- ✓ Superior heat reflection
- ✓ Suitable for any roof geometry
- ✓ Approved for Green Roofs (Roof-Resistant)
- ✓ Available in a range of colours

PRODUCT NAME:

EVALON[®] VSK

EVA - synthetic roofing membrane according to EN 13956

MANUFACTURER/ DISTRIBUTOR:

alwitra[®] GmbH & Co. Klaus Göbel
Am Forst 1
D – 54296 Trier

PLACE OF PRODUCTION:

Factory Hermeskeil

KIND OF INSTALLATION:

As waterproofing of non-used flat and pitched roofs. Manufacturer's installation instruction must be strictly observed.

FPC CERTIFICATE NO:

1343 - BPR - 06-1432

FPC ISSUE OF CERTIFICATION:

06

EUROPEAN STANDARD:

EN 13956

PRODUCT DESCRIPTION:

Bitumen compatible EVA-roofing membrane, with effective homogeneous sealing thicknesses (1,2 mm / 1,5 mm) and polyester fleece-backing, produced in different colours.

STANDARD MEMBRANE

DIMENSIONS:

Length: 25m

Widths: 1,05m, 1,55m

Thicknesses: 1,2mm / 1,5mm sealing thickness + backing, further thicknesses on request

Evalon[®] VSK

Superior Single-Ply Waterproofing

PROPERTY	TESTING METHOD	UNIT (LIMIT DEVIATION)	VALUE	RESULTS
External fire performance ^a	ENV 1187 DIN 4102-7		Passed	class BROOF (t1) + (t3) + (t4) ^b
Reaction to fire	EN 13501-1		class E	EN 13501-1
Water tightness	EN 1928 method B	kPa	≥ 400	MLV
Joint peel resistance	EN 12316-2	N/50 mm	≥ 150 ^c	MLV
Joint shear resistance	EN 12317-2	N/50 mm	≥ 400 ^c	MLV
Max. tensile force	EN 12311-2	N/50 mm	≥ 500	MLV
Elongation at max.tensile force	EN 12311-2	%	≥ 60	MLV
Resistance to impact load	EN 12691 method A	mm	≥ 300	MLV
Resistance to static load	EN 12691 method B	kg	≥ 20	MLV
Tear resistance	EN 12310-1 EN 12310-2	N N	≥ 300 ≥ 150	MLV
Dimensional stability	EN 1107-2	%	≤ 1	MLV
Low temperature flexibility	EN 495-5	°C	≤ -30	MLV
UV exposure	EN 1297	visual control		passed
Hail resistance	EN 13583	m/s	≥ 30	MLV
Water vapour permeability	EN 1931	μ (± 30%)	+/- 20.000	MDV
Bitumen compatibility	EN 1548 method (b)			passed
Durability (UV exposure, high temperatures and water)	EN 1297	visual control		passed
Liquid chemicals, including water	on request			
Resistance to root penetration d	EN 13948			passed

INFORMATION FOR THE USER

a. Tested according to DIN 4102-7 or ENV 1187-1 with different layer impacts. Therewith the requirement is fulfilled in Germany.

b. Valid for the respective tested build-up

c. Hot air welding

MLV = manufacturer's limiting value

MDV= manufacturer's declared value

Disclaimer: The preceding information, in particular the recommendations for the handling and use of our products, are based on our knowledge and experience in normal cases, providing that the products have been properly stored and used. Owing to different materials, subsurfaces and differing working conditions, we cannot guarantee a specific result or accept liability, irrespective of the legal position, substantiated neither by this information nor by verbal advice, unless we can be shown to be guilty of wilful intent or gross negligence. In this event, the user has to provide evidence that he has provided in writing all the notices required by alwitra for a proper and positive assessment to alwitra in good time and in full relating to this assessment. The user has to check the products for their suitability for the intended application. We re-reserve the right to make modifications to the product specification without notice. The trademark rights of third parties should be observed. In all other respects our general terms and conditions of business apply. The most recent local product datasheet also applies, which should be requested from us.