



Fleet Glass Primer

Fleet Glass Primer is a primer used as a bonding agent between glass substrates and Fleet waterproofing or thick-film systems.

PROPERTIES AND ADVANTAGES

- Very good bonding properties between glass and Fleet systems applied on top
- Easy to apply

AREAS OF APPLICATION

Fleet Glass primer is used as a bonding agent between glass substrates and Fleet waterproofing or thick-film systems applied on top. Not suitable for overcoating with any other products (e.g. primer, finish, surfacer/filler, mortar).

COLOURS

Fleet Glass primer is unpigmented

PACKAGING

1kg tin

PRODUCT FEATURES

MATERIAL:

1-component, solvent-free, acrylate-based primer

STORAGE

Store products sealed in their original airtight container and in a cool, dry and frost-free place. Unopened products have a shelf life of at least 6 months. Direct sunlight on the containers should be avoided, including on site. After removing some of the contents, reseal the containers so they are airtight.

APPLICATION CONDITIONS

TEMPERATURES:

The product can be applied within the following temperature ranges:

PRODUCT	TEMPERATURE RANGE IN °C		
	Air	Substrate*	Material
Fleet Glass Primer	+3 to +35	+3 to +50*	+3 to +30

* The substrate temperature must be at least 3°C above the dew point during application and curing

01202 785 200

info@icbwatertight.co.uk

icbwatertight.co.uk

UK Head Office, Unit 9-11 Fleets Industrial Estate Willis Way, Poole, Dorset BH15 3SU



MOISTURE

- The relative humidity must be \leq 90%.
- The surface to be coated must be dry and ice-free.
- The surface must be protected from moisture until the coating has dried.

REACTION TIMES

TEMPERATURE	FLEET PRIMER M
30°C	least 1 hour
20°C	at least 2 hours
10°C	at least 3 hours
3°C	at least 4 hours

CONSUMPTION RATES	0.15 – 0.20 kg/m ²
TECHNICAL DATA	Density: 1.00g/cm ³

PRODUCT APPLICATION; EQUIPMENT / TOOLS

For applying the product:

- Finishing roller (sheepskin roller, minimal shedding)
- Brush

SUBSTRATE PREPARATION

Use a lint-free cloth and Fleet Cleaning Agent to wipe down the glass surface before applying the product.

MIXING

Stir or shake the primer thoroughly before application.

APPLICATION

Use a finish roller to apply an even coat of the primer to the substrate. Avoid excess build-up of material in all areas, and especially in corners. If necessary, use a brush to spread the material evenly and avoid greater layer thicknesses. The primer should be overcoated with the next Fleet products within 24 hours of its application. If this is impossible, the primer has to be removed with Fleet Cleaning Agent and then reapplied.

CLEANING

If work is interrupted or when it is completed, clean the tools thoroughly with Fleet Cleaning Agent. This can be done with a brush. Do not use the tools again until the Cleaning Agent has evaporated fully.

01202 785 200

info@icbwatertight.co.uk

icbwatertight.co.uk

UK Head Office, Unit 9-11 Fleets Industrial Estate Willis Way, Poole, Dorset BH15 3SU



INFORMATION ON SAFETY AND RISK

Please refer to the safety data sheets for the products used. Refer to Material Safety Data sheet for disposal information.

The above information, especially information about application of the products, is based on extensive development work as well as many years of experience and is provided to the best of our knowledge. However, the wide variety of requirements and conditions on site mean that it is necessary for the product to be tested to ensure that it is suitable for the intended purpose. Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology or improvements to our products.