



Fleet Primer A2

Fleet Primer A2 is a fast-reactive primer used as a barrier on asphalt substrates in preparation for the later application of Fleet waterproofing or surfacing products.

PROPERTIES AND ADVANTAGES

- Very good adhesion to asphalt substrates
- Easy to apply
- Can also be applied at sub-zero temperatures
- Hydrolysis- and alkali-resistant
- Fast-curing
- Solvent-Free

AREAS OF APPLICATION

Fleet Primer A2 is used for the pre-treatment (primer and barrier coat) of asphalt substrates (e.g. mastic asphalt) ready for the later application of Fleet waterproofing or surfacing products.

PRODUCT FEATURES	
MATERIAL: 2-component, fast-reactive / flexibilised PMMA-based (polymethyl methacrylate) resin primer	
PACKAGING	
SUMMER: 10.00 kg Fleet Primer A2 <u>0.30 kg</u> Catalyst (3 x 0.1 kg) 10.30 kg	WINTER: 10.00 kg Fleet Primer A2 <u>0.60 kg</u> Catalyst (6 x 0.1 kg) 10.60 kg

COLOURS

Fleet A2 Primer is available in the following standard colours:

- Clear (unpigmented, slightly yellowish)
- White

STORAGE

Store products sealed in their original airtight container and in a cool, dry and frost-free place. Unopened products have a shelf life of at least 6 months. Direct sunlight on the containers should be avoided, including on site. After removing some of the contents, reseal the containers so they are airtight.



APPLICATION CONDITIONS

TEMPERATURES

The product can be applied within the following temperature ranges:

PRODUCT	TEMPERATURE RANGE IN °C		
	AIR	SUBSTRATE*	MATERIAL
Fleet Primer A2	-5 to +35	-5 to +50*	+3 to +30

* The substrate temperature must be at least 3°C above the dew point during application and curing

During application and curing. The substrate temperature must not be less than +3°C if a topping is applied to the surface (see "Preparation for subsequent layers"). Reaction problems can occur at lower temperatures.

MOISTURE

- The relative humidity must be ≤ 90%.
- The surface to be coated must be dry and ice-free.
- The surface must be protected from moisture until the coating has hardened.

REACTION TIMES AND REQUIRED AMOUNTS OF CATALYST

		FLEET PRIMER A2 (at 20°C, 3% catalyst)
POT LIFE		approx. 15 minutes
RAIN-PROOF AFTER		approx. 30 minutes
CAN BE WALKED ON / OVERCOATED AFTER		approx. 45 minutes
CURING TIME		approx. 3 hours

Higher temperatures or greater proportions of catalyst will reduce reaction times, while lower temperatures and smaller proportions of catalyst will increase reaction times.

The following table indicates the recommended amount of catalyst required to adjust the curing reaction to the temperature.

PRODUCT	Substrate temperature in °C; required amounts of catalyst in % w/w (guide)												
Fleet Primer A2	-10	-5	+3	5	10	15	20	25	30	35	40	45	50
	N/A	6%	6%	6%	4%	4%	2%	2%	2%	2%	1%	1%	1%





CONSUMPTION RATES	SUBSTRATE	CONSUMPTION
	Smooth	0.40kg/m ²
	Fine-sandy	0.50kg/m ²
	Rough	0.80kgm ²
TECHNICAL DATA	Density clear	1.03g/cm ³
	Density white	1.08g/cm ³

PRODUCT APPLICATION; APPLICATION EQUIPMENT/TOOLS

For mixing the product:

- Twin-paddle stirrer

For applying the product:

- Sheepskin roller
- Brush (only for areas not accessible with a roller)

SUBSTRATE PREPARATION

The Primer must only be applied to a prepared substrate. Please refer to the appropriate application guide for information about correct surface preparation.

MIXING

- First stir the tub contents thoroughly.
- Then add the catalyst while stirring the resin at the slow-speed setting and mix for 2 minutes. Make sure that the product on the base and sides of the container is mixed in.
- At product temperatures < 10°C the product should be stirred for 5 minutes, as the catalyst will take longer to dissolve

APPLICATION

Use the sheepskin roller to apply an even film-forming coat of primer. Avoid creating puddles of primer. Once the coating is cured, apply a second coat to cover any defects (bubbles, areas not fully coated)

PREPARATION FOR SUBSEQUENT LAYERS

For the subsequent application of Fleet Mortar: Once the primer has hardened, apply a second layer and top with a little quartz sand (0.1-0.2 kg/m² at 0.2-0.6mm) while the primer is still wet. The sand topping creates the necessary key, i/e roughness. for application of the mortar. **Never apply the topping to the first coat primer.**



CLEANING

If work is interrupted or when it is completed, clean the tools thoroughly with Fleet Cleaning Agent within the pot life of the material (approx. 10 minutes). This can be done with a brush. Do not use the tools again until the Cleaning Agent has evaporated fully. Simply immersing the tools in the Cleaning Agent will not prevent the material from hardening.

INFORMATION ON SAFETY AND RISKS

Please refer to the safety data sheets for the products used. Refer to Material Safety Data sheet for disposal information.

GENERAL INFORMATION

The above information, especially information about application of the products, is based on extensive development work as well as many years of experience and is provided to the best of our knowledge. However, the wide variety of requirements and conditions on site mean that it is necessary for the product to be tested to ensure that it is suitable for the intended purpose. Only the most recent version of the document is valid. We reserve the right to make changes to reflect advances in technology or improvements to our products.