



STRATABASE SBS

**Bituminous plastomeric torch-on waterproofing membranes
Sbs modified – cold flexibility -15°C – spunbond polyester reinforcement**

PROFILE

STRATABASE-SBS consist of a special compound based on distilled bitumen modified with selected elastomers and reinforced with a non-woven spunbond polyester reinforcement, which offers good characteristics of mechanical resistance, ultimate elongation and dimensional stability.

The SBS modified waterproofing compound assures good flexibility at low temperatures and excellent properties of elongation and resistance to roof movements.

The whole ICB range of products is manufactured under a closely controlled system which conforms to the ISO 9001 requirements and guidelines.

INSTALLATION

The underside of STRATABASE-SBS is finished with a thin thermofusible film, which easily melts upon torching, favouring a rapid and clean application.

Surfaces must be perfectly dry, clean and sufficiently plain or levelled. Prior to adhering the membrane to the substrate, the latter must be primed with a quality bituminous primer. The product is welded down using a propane gas burner which burns off the underside film and melts down part of the bituminous undercoating. Overlaps have to be welded by torching with side laps of 8-10cm and end laps of 12-15 cm.

Stop installation in rain, snow, heavy fog or if the air temperature falls below +0°C .

HANDLING AND STORING

When unloading the material avoid any abrupt impact with the ground.

Do not take up the rolls to the roof without using supporting pallets and safety equipment.

Always store the rolls in an upright position, preferably under shelter. In the cold season, if possible, do not stock the product on site during the night-time.

In case of double stacking, use a rigid separation board to spread the load.



USES

STRATABASE-SBS is versatile and easy to install. Because of their good mechanical characteristics and high dimensional stability, they are suitable to be used both in residential and industrial waterproofing.

STRATABASE-SBS is compatible with most materials normally used in roofing structures.

TECHNICAL DATA

			STRATABASE-SBS	
EN Norms	Features	Units	Nominal Values	Tolerances
EN 1848-1	LENGTH	m	8	> as/declared
EN 1848-1	WIDTH	m	1	-0,5%
EN 1849-1	THICKNESSmm	n/a	± 0,2	
EN 1849-1	WEIGHT kg/m ²		3,0	
EN 12311-1	TENSILE STRENGTH long. (max. charge)	N/50mm	400	-20%
	TENSILE STRENGTH trans.(max. charge)	N/50mm	300	-20%
EN 12311-1	ELONGATION AT BREAK longitudinal	%	40	-15pp
	ELONGATION AT BREAK transversal	%	-15pp	40
EN 12310-1	TEARING RESISTANCE longitudinal	N	140	
	TEARING RESISTANCE transversal	N	140	
EN 12730	STATIC PUNCTURING	kg	10	
EN 12691	DYNAMIC PUNCTURING	mm	1000	
EN 1107-1	DIMENSIONAL STABILITY	%	conforms to UNI 8629	
EN 1109	COLD FLEXIBILITY	°C	-15	
EN 1110	HEAT RESISTANCE	°C	100	
EN 1928	WATER TIGHTNESS	Kpa	> 60	
EN 1928	WATER RESISTANCE (max. variation)	%	± 2	

PRODUCT	WEIGHT	DIMENSIONS	ROLLS
	(kg/sqm)		/PALLET
STRATABASE-SBS	3,0 KG	1 Roll 1 x 8 mt	36

